

In-Situ Infrared Transmission Study of Rb- and K-Doped Fullerenes

Michael C. Martin, Daniel Koller, L. Mihaly

Department of Physics, State University of New York at Stony Brook, Stony Brook, NY 11794-3800

(23 December 1992)

We have measured the four IR active C_{60} molecular vibrations in M_xC_{60} ($M = K, Rb$) as a function of doping x . We observe discontinuous changes in the vibrational spectra showing four distinct phases (presumably $x = 0, 3, 4$, and 6). The $1427cm^{-1}$ and $576cm^{-1}$ modes show the largest changes shifting downward in frequency in four steps as the doping increases. Several new very weak modes are visible in the $x = 6$ phase and are possibly Raman modes becoming weakly optically active. We present quantitative fits of the data and calculate the electron-phonon coupling of the $1427cm^{-1}$ IR mode.

PACS: 74.70Wz, 63.20Kr, 74.25Kc

The discovery of superconductivity in alkali doped C_{60} [1] has prompted a great deal of excitement and a large body of research. Since electron-phonon coupling proved to be responsible for superconductivity in many materials, the relation between the charge carriers and the lattice vibrations is important. Here we present a study of the infrared active molecular vibrations of M_xC_{60} as a function of alkali metal doping, x , for ($M = K$ and Rb). We show, for the first time, the shift of some IR modes to lower frequencies in discrete steps, corresponding to the four known stable phases, $x = 0, 3, 4, 6$. We also perform an analysis of how the change in the vibrational modes is related to the introduction of carriers into the lowest unoccupied molecular orbital band of C_{60} .

The truncated icosohedral structure of C_{60} fullerenes belongs to the icosohedral point group, I_h , and has four infrared active intramolecular vibrational modes with F_{1u} symmetry [2]. These modes, with center frequencies $\nu_1 = 527, \nu_2 = 576, \nu_3 = 1182$, and $\nu_4 = 1427$ have been experimentally observed [3,4]. The 527 and $576cm^{-1}$ modes are associated with primarily radial motion of the carbon atoms while the 1182 and $1427cm^{-1}$ modes are primarily tangential motion [2].

In the M_xC_{60} compounds, the alkali atoms give up one electron each to the lowest unoccupied molecular orbital (LUMO) of a C_{60} molecule. As long as the on site Coulomb repulsion is not too large the triply degenerate t_{1u} LUMO can hold six electrons [5]. Therefore the t_{1u} orbital is half filled by three electrons, and the material is metallic and superconducts at low temperatures [1]. Completely filling the t_{1u} orbital with six electrons makes the C_{60} a band insulator and the structure becomes body-centered-cubic [6]. An insulating phase at $x = 4$ has also been observed with a body-centered-tetragonal structure [7].

The C_{60} for this study was prepared using the well

known technique of Kratschmer *et. al.* [4]. The resultant fullerene powder was loaded into a tantalum boat and heated to about $500^\circ C$ in a vacuum of $\sim 1 \times 10^{-6}$ Torr to vapor deposit C_{60} inside the sample cell. Film thickness was monitored by counting visible light interference fringes as the C_{60} was deposited. Typical sample thickness was about $1.2\mu m$.

Our miniature sample cells are constructed of glass with two silicon windows, one of which serves as a substrate for the C_{60} . A small appendage contains the alkali metal and the entire sample chamber is sealed under high vacuum. The transmission spectra were obtained with a Bomem *MB-155* FTIR spectrometer at $2cm^{-1}$ resolution covering a $400 - 6000cm^{-1}$ frequency range as the sample was doped. Four-probe resistivity of the film was measured simultaneously. By carefully warming the alkali metal to increase the vapor pressure and by heating the C_{60} film to increase the diffusion rate of the metal into the film, a slow, continuous doping was achieved. During potassium doping, the substrate was maintained at $120^\circ C$ and the metal at $100^\circ C$. For Rb , the corresponding temperatures were $85^\circ C$ and $70^\circ C$ respectively. The infrared spectra were obtained with the film samples at their substrate temperatures.

The results of the infrared spectroscopy *in-situ* with alkali metal doping are displayed in Figures 1 and 2. Since at low frequencies the transmitted intensity is roughly proportional to the square of the resistivity, the IR measurement by itself is a good indicator of the doping process. Indeed, both the DC resistivity and the transmission exhibit a minimum as the doping proceeds. Kochanski *et. al.* associate this minimum with the metallic M_3C_{60} phase [8]. Upon further doping, the resistivity reaches a maximum, corresponding to the insulating M_6C_{60} phase, after which the resistivity drops, but the features in the spectra change little, indicating that we are now just coating the sample with alkali metal and the C_{60} is fully doped ($x = 6$). At this stage, closer visual inspection reveals metallic films on the window surfaces.

We have performed quantitative fits to both sets of doping data. The vibrational spectra are accurately fit using a dielectric function composed of Lorentzian oscillators and a dc conductivity to mimic the changing conductivity observed as doping progresses. This yields the center frequency, ω_0 , strength, S , and width, Γ , of each mode. We present the results and our assignments of corresponding phases in Table I. We interpret the data as follows: as the doping proceeds, layers of M_3C_{60} grow followed by similar layers of M_4C_{60} and M_6C_{60} . We observe that the ν_1 mode at $526cm^{-1}$ gets weaker as the

sample loses all $x = 0$ phase and reappears at 468cm^{-1} in the $x = 6$ phase. The ν_2 mode shifts in discrete steps and grows in strength during the doping process. This is most clearly visible for the *Rb* doping where we see it shifts from 576 to 573 to 570 to 565cm^{-1} . Using the x -ray results [9,10,7,6] which indicate that only the $x = 0, 3, 4$, and 6 phases are stable at this temperature, we associate these modes with the $x = 0, 3, 4$, and 6 phases respectively. The ν_3 mode at 1182cm^{-1} is enhanced by a factor of almost 2 in the $x = 6$ phase. Looking at the ν_4 mode, we can again see distinct phases. This mode is enhanced by a factor of 80 in the $x = 6$ phase.

The shifts in the ν_2 and ν_4 modes for the K doped sample show only three clear phases. This may be due to more uniform doping of the K_xC_{60} sample, as it is known that K diffuses more rapidly into C_{60} than *Rb* [11]. Vibrational modes are more difficult to detect in a homogeneous metallic film since the high reflectivity, due to conduction electrons, dominates the response.

The resultant values for our $x = 6$ data are in excellent agreement with previous IR measurements on M_6C_{60} published by Fu *et. al.* [12]. The phase separation seen in our data is also in agreement with previous Raman spectroscopy results [11,13] where, for example, the change in the $A_g(2)$ pinch mode originally at 1458cm^{-1} clearly shows distinct phase separation. Note that this mode, like the ν_4 mode in the IR spectrum, involves stretching of the $C = C$ double bonds.

The *Rb* $_6C_{60}$ and *K* $_6C_{60}$ spectra also show some very weak modes at $1461, 1418, 1317, 1284, 1240, 1190, 1146, 943, 688, 645$ and 532cm^{-1} . These are similar in frequency to several Raman active modes for C_{60} ($1458, 1430, 1396, 1315, 1241, 1190, 1140, 950$, and 533cm^{-1}) and *Rb* $_6C_{60}$ ($1477, 1431, 1322, 1235, 1121, 1091, 689$, and 655cm^{-1}) [11,14,15]. We may be observing Raman modes becoming weakly IR-active in our fully doped samples. Some of these modes are not allowed by the symmetry of the single molecule, but they have been observed in Raman spectra of crystalline C_{60} [14,15]. It should be noted that the changes in the vibrational modes due to photoexcitation of carriers [16] are different from the changes reported here for chemical doping.

The charged-phonon theory by M. J. Rice and Han-Yong Choi [17] predicts many of the features we observe, in particular, the enhancement of the strength and the softening of the 1428cm^{-1} mode upon doping. In Figure 3 we illustrate how the addition of electrons to a complex molecule can enhance the strength of a "silent" IR active phonon. Figure 3 (a) depicts an eigenmode of the molecule, characterized by two pairs of atoms oscillating in opposite phase. This mode is "IR active" in the sense that it has odd symmetry. However, as long as only symmetric electronic states are allowed, the mode is "silent" since there is no net dipole moment in the direction of the electric field. In Figure 3 (b) we allow for asymmetric states, i.e. electron transfer between the two pairs of atoms. The electron transfer naturally couples to the atomic displacements via the rearrangement of electronic

states, and it also generates an electric dipole moment. Rice and Choi [17] argue that in C_{60} , electrons excited between the between the t_{1u} and the next higher energy t_{1g} molecular orbitals create a coupling to the infrared active vibrational modes, and simultaneously soften the vibration frequency (Figure 4). In view of the agreement between the experiment and theory for the ν_4 mode, it is all the more surprising that the ν_1 mode does not follow the same behavior. We argue that this mostly radial mode is more sensitive to the inter-molecular forces, and its frequency is influenced by the FCC to BCC phase transition.

As long as the electron is confined to a single molecule, symmetry arguments predict that the intraband electron-phonon scattering, relevant to superconductivity, is dominated by Raman modes. Therefore, the attempts to explain superconductivity in the fullerenes focussed on the Raman active A_g and H_g modes [18]. However, for extended electronic or vibrational states, the IR modes may become important too. In fact, we see evidence for damping of the vibrational modes by conduction electrons. According to the sum rule, $\sum_i \Gamma_i / \omega_{0i}^2 = (\pi/2)N(E_F)\lambda$ [19], the broadening of the vibrational mode is related to the electron-phonon coupling. The largest change, 16.3cm^{-1} , in the widths was observed in the ν_4 mode. This leads to a contribution of 0.055 states/eV in $N(E_F)\lambda$, for each of the three degenerate modes. Considering that there are 180 vibrational modes for the C_{60} molecule, a coupling of this magnitude is significant although the strongest electron-phonon coupling seen to date is for the $H_g(2)$ Raman mode (0.25 states/eV) [15]. It remains to be seen how important this coupling is for superconductivity.

In summary, we have measured the four infrared active intramolecular vibrational modes of C_{60} as a function of *Rb* and *K* doping. Quantitative presentation of our measurements and assignments of the modes to different stable phases of M_xC_{60} were made. We show that our results are consistent with previous works and describe how our data could relate to a superconducting pairing mechanism in these materials.

ACKNOWLEDGMENTS

This work was supported by NSF grant DMR9202528. We would like to thank P. B. Allen, G. L. Carr and K. Holczer for valuable discussions. Thanks to J. Marecek of the SUNY at Stony Brook chemistry department for C_{60} separation and purification and to J. Kirz and S. Lindaas for the use of high vacuum equipment.

[1] A.F. Hebard *et. al.*, Nature **350**, 600 (1991); K. Holczer

- et. al.*, Science **252**, 1154 (1991); M. J. Rosseinsky *et. al.*, Phys. Rev. Lett. **66**, 2830 (1991)
- [2] R. E. Stanton and M. D. Newton, J. Phys. Chem. **92**, 2141 (1988); Z. C. Wu *et. al.*, Chem. Phys. Lett. **137**, 291 (1987)
- [3] W. Kratschmer, K. Fostiropoulos, D. R. Huffman, Chem. Phys. Lett. **170**, 167 (1990); W. Kratschmer *et. al.*, *Dusty Objects in the Universe*, eds E. Bussoletti, A. A. Cittone, Kluwer, Dordrecht 1991; S. Bethune *et. al.*, Chem. Phys. Lett. **179**, 181 (1991)
- [4] W. Kratschmer, L. D. Lamb, K. Fostiropoulos, D. R. Huffman, Nature **347**, 354 (1990)
- [5] R.C. Haddon, Acc. Chem. Res. **25**, 127
- [6] O. Zhou *et. al.*, Nature **351**, 462 (1991)
- [7] R. M. Fleming *et. al.*, Nature **352**, 701 (1992); Peter W. Stephens, *et. al.*, Phys. Rev B **45**, 543 (1992)
- [8] G. P. Kochanski, A. F. Hebard, R. C. Haddon, A. T. Fiory, Science **255** 184 (1992)
- [9] R. M. Fleming *et. al.*, Mater. Rs. Soc. Symp. **206**, 691 (1991)
- [10] P. W. Stephens *et. al.*, Nature **351**, 632 (1991)
- [11] S. J. Duclos, R. C. Haddon, S. Glarum, A. F. Hebard, K. B. Lyons, Science **254**, 1625 (1991)
- [12] K.-J. Fu *et. al.*, Phys. Rev. B **46** 1937 (1992)
- [13] T. Pichler, M. Matus, J. Kurti, and H. Kuzmany, Phys. Rev. B **45**, 13841 (1992)
- [14] P.H.M. van Loosdrecht, P.J.M. van Bentum, and G. Meijer, Phys. Rev. Lett. **68**, 1176 (1992)
- [15] Michael G. Mitch, Sabrina J. Chase, and Jeffrey S. Lanin, Phys. Rev. Lett. **68**, 883 (1992)
- [16] G. Lawrence Carr, Michael C. Martin, D. Koller, L. Mihaly, to be published; Y. H. Kim, F. Li, F. Diederich, Phys. Rev. B **45**, 10169(1992)
- [17] M. J. Rice and H.-Y. Choi, Phys. Rev. B **45**, 10173 (1992)
- [18] R. A. Jishi, M.S. Dresselhaus, Phys. Rev. B **45**, 2597 (1992); M. Schluter *et. al.*, Phys. Rev. Lett. **68**, 526 (1991); C. M. Varma, J. Aanan, K. Raghavachari, Science **254**, 989 (1991); F. C. Zhang, M. Ogata, T. M. Rice, Phys. Rev. Lett. **67**, 3452 (1991)
- [19] P. B. Allen, in *Dynamical Properties of Solids*, eds G. K. Horton and A. A. Maradudin (North Holland, New York, 1980), Vol. 3, p. 95

FIG. 1. Rb_xC_{60} infrared transmission spectra as a function of x . (a) shows the lower two vibrational modes (ν_1 and ν_2) and (b) shows the upper two modes (ν_3 and ν_4). The curves are offset for clarity. Undoped C_{60} is the top curve and the sample is further doped going down in the figure. The bottom curve is for fully doped Rb_6C_{60} . The minimum in the resistivity of the sample corresponds to the curve labeled 'min'. Vertical lines are guides to indicate the assignments of vibration frequencies, as obtained from numerical fits.

FIG. 2. The same as Figure 1 now for K_xC_{60} .

FIG. 3. Schematic illustration of charge-transfer induced infrared activity. The arrowed circles represent atoms moving withing a single "molecule"; the symmetry of the oscillation is odd. In (a) only even electronic states are allowed and therefore the strength of the IR active vibration is small. In (b), the electron transfer couples the mode to the external field by introducing a dipole moment.

FIG. 4. The frequency of the ν_4 IR mode vs. the inferred composition for Rb doped C_{60} . Circles refer to the calculation of Rice and Choi (Ref. [15]).

TABLE I. Lorentzian oscillator fits to the four IR intramolecular vibrations of M_xC_{60} ($M = Rb$ and K) assigned to the different stable phases ($x = 0, 3, 4, 6$). The numbers are essentially the same for both dopants except (^a) as noted. ω_0 is the center frequency, S is the strength ($S = \omega_p^2/\omega_0^2$), and Γ is the width of each vibrational mode.

		C_{60}	M_3C_{60}	M_4C_{60}	M_6C_{60}
ν_1	$\omega_0(cm^{-1})$	526		472	467
	S	.02		.008	.03
	$\Gamma(cm^{-1})$	2.5		1.5	3
ν_2	$\omega_0(cm^{-1})$	576	573	570	565
	S	.008	.019	.022	.17
	$\Gamma(cm^{-1})$	2.7	3	3.7	2.8
ν_3	$\omega_0(cm^{-1})$	1182			1182
	S	.0018			.003
	$\Gamma(cm^{-1})$	4.2			5.8
ν_4	$\omega_0(cm^{-1})$	1428	1393	1363 ^a	1340
	S	.001	.012	.016	.08
	$\Gamma(cm^{-1})$	4.5	20.8	23	7.2

^aValues in table are for Rb_4C_{60} . K_4C_{60} differs for ν_4 : $\omega_0 = 1369cm^{-1}$, $S = .028$, and $\Gamma = 21cm^{-1}$.